

CEL-SPAN®



# Process Enhancer 332

---

## Cel-Span® Process Enhancer 332

A non-clear compounded product that protects film resin during high temperature processing.

Cel-Span® Process Enhancer 332 is a non-clear compounded product containing a high level of thermal stabilizers and  $\text{CaCO}_3$  to provide protection of film resins during high temperature extrusion and lamination processes, thus maximizing inherent physical properties of the natural al resins. CelSpan® Process Enhancer 332 eliminates build up in both internal and external metal surfaces of the extrusion die, as well as reduction of wrinkles in thin gauge films. This product will extend  $\text{Tio}_2$  up to 5% without loss of opacity.

### **Applications: Film**

Melt Flow: 1.0 dg /10min.

Blend Density: 1.25 g/cc

Pellet Size: 1/8" round pellet

Color: Beige/Natural

Pellet/Gram: 35/45

### **Features and Benefits:**

Cel-Span® Process Enhancer 332 is an effective masterbatch for polyolefins especially HDPE, LDPE and LLPDE used to enhance physical properties of the natural resin like puncture resistance, tear propagation, and anti-blocking properties coupled with excellent thermal stabilization and reduction of wrinkles.

Cel-Span® Process Enhancer 332 is also recommended to heat stabilize and reduce die build up of lamination films exceeding 600F and above.

The product is used at a 3%-5% level in LDPE or LLDPE film resins to reduce or eliminate die lines and build up on internal and external die metal surfaces Cel-Span® Process Enhancer 332 additives are listed on the TASCA list.

There are no adverse health effects from the use of Cel-Span® Process Enhancer 332.

Cel-Span® Process Enhancer 332 is packaged in 55 lb. plastic bags or 1,100 lb. gaylord boxes. We recommend this product be kept closed and stored in the original container, away from light, heat, and highly humid environments.

Disclaimer - This data contains general Information and describes typical properties only. Only persons qualified to determine for themselves the suitability of our products for particular purposes should evaluate its potential uses. No guarantee is made or liability assumed, the application of this data and the products describes herein being at the sole risk of the user. Samples are provided to the requestor on an "AS IS, WHERE IS" evaluation purpose only basis, solely under the use and direction of the requestor, without warranty of any kind (either express or implied), including but not limited to any implied warranties of merchantability and fitness for a specific or general purpose and those arising by statute or by law, or from a cause of dealing or usage of trade. In no event, regardless of cause, shall AxiPolymer be liable for any indirect, special, incidental, punitive or consequential damages of any kind, whether arising under breach of contract, tort (including negligence), strict liability or otherwise, and whether based on this agreement or otherwise, even if advised of the possibility of such damages.